

**NORDIC WOOD PRESERVATION COUNCIL – NWPC**

Technical Expert Group

c/o Danish Technological Institute, Wood Technology

Att. Niels Morsing

Gregersensvej, DK 2630 Taastrup, Denmark

Phone: +45 72 20 23 12

E-mail: nmo@teknologisk.dk



Date: 2020-01-01

List no 98

**Wood preservatives and other wood protection systems approved by the Nordic Wood Preservation Council\*\*\***

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m <sup>3</sup> Class**				Approval valid until	Certificate No
	M	A	AB	B		
<b>WATER-BORNE TYPE</b>						
<b>CB + triazole products</b>						
Tanalith E-7/Tanalith E 3492	-	16.0	8.0	-	2020-12-31	168
Tanalith E3463/E3475		20.0	10.0		2023-12-31	200
Bochemit Forte Profi		22.0	14.0		2022-12-31	205
<b>ACQ products</b>						
Impralit-ACQ 1900	-	36.0	19.0	-	2022-12-31	87
Celcure AC 800	-	36.0	19.0	19.0	2022-12-31	181
Impralit-ACQ 2200	-	22.0	12.0	-	2020-12-31	175
Celcure AC 500	-	25.0	12.0	-	2020-12-31	183
impralit-KDS 4	-	28.0	15.0	-	2020-12-31	154
Impralit-KDS	-	14.0	8.0	-	2020-12-31	203
Celcure C4	-	20.0	10.0	-	2020-12-31	197
Celcure M65	-	22.0	11.0	-	2024-12-31	202
Korasit KS2	-	22.0	12.0	-	2020-12-31	204
<b>Quaternary ammonium products</b>						
Impralit-BKD	-	-	10.0	-	2020-12-31	171
<b>Triazole products</b>						
Wolsit KD-10	-	-	11.0	3.5	2022-12-31	185
<b>Other water-borne products</b>						
Wolmanit CX-8	-	18.0	9.0	9.0	2020-12-31	162
Wolmanit CX-8N	-	18.0	9.0		2022-12-31	199
Wolmanit CX-8WB	-	18.0	9.0		2020-12-31	191
Wolmanit CX-10		15.0	7.0	7.0	2020-12-31	176

\* The retention figure refers to the formulation specified by the preservative manufacturer.

\*\* The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

\*\*\* Wood protection systems are approved according to the NWPC approval system. The approval according to BPR (Biocidal Products Regulation) is done by the European and national authorities. NWPC do not take any responsibility with respect to the BPR approval.

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m <sup>3</sup> Class**				Approval valid until	Certificate No
	M	A	AB	B		
<b>ORGANIC SOLVENT TYPE</b>						
<b>Triazole products<sup>¤</sup></b>						
Protim P-Vac 11	-	-	-	26.0/0.41 a.i.	2020-12-31	187
<b>Triazole + IPBC products<sup>¤</sup></b>						
Gori 605	-	-	-	23.0/0.23 a.i.	2020-12-31	189
<b>CREOSOTE OILS</b>						
Creosote grade A	400	120	80	-	running	EN 13991
Creosote grade B	400	110	80	-	running	EN 13991
Creosote grade C	400	100	70	-	running	EN 13991
MT-kreosot	400	110	80	-	2022-12-31	134
<b>MODIFIED WOOD</b>						
ThermoTreat v 2.0			>170° Min 1,5 hr	>170° Min 1,5 hr	2022-12-31	206

<sup>¤</sup> The retention requirement is uptake of the formulation/active ingredients (a.i.) in kg per m<sup>3</sup> sapwood in the treated zone.