

NORDIC WOOD PRESERVATION COUNCIL – NWPC

Technical Expert Group
 c/o Danish Technological Institute, Wood Technology
 Att. Niels Morsing
 Gregersensvej, DK 2630 Taastrup, Denmark
 Phone: +45 72 20 23 12
 E-mail: nmo@teknologisk.dk



Date: 2018-01-01

List no 95

Wood preservatives approved by the Nordic Wood Preservation Council

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³ Class**				Approval valid until	Certificate No
	M	A	AB	B		
WATER-BORNE TYPE						
CC products						
Impralit CK	26.0	19.0			2020-12-31	194
Korasit CC	26.0	19.0	-	-	2022-12-31	186
CB + triazole products						
Tanalith E-7/Tanalith E 3492	-	16.0	8.0	-	2020-12-31	168
Tanalith E3463/E3475		20.0	10.0		2018-12-31	200
Bochemit Forte Profi		22.0	14.0		2022-12-31	205
ACQ products						
IMPRALIT ACQ 1900	-	36.0	19.0	-	2022-12-31	87
Celcure AC 800	-	36.0	19.0	19.0	2022-12-31	181
ACQ 2200	-	22.0	12.0	-	2020-12-31	175
Celcure AC 500	-	25.0	12.0	-	2020-12-31	183
impralit-KDS 4	-	28.0	15.0	-	2020-12-31	154
Impralit-KDS	-	14.0	8.0	-	2020-12-31	203
Celcure C4	-	20.0	10.0	-	2020-12-31	197
Celcure M65	-	22.0	11.0	-	2019-12-31	202
Korasit KS2	-	22.0	12.0	-	2020-12-31	204
Quaternary ammonium products						
Impralit-BKD	-	-	10.0	-	2020-12-31	171
Triazole products						
Wolsit KD-10	-	-	11.0	3.5	2022-12-31	185
Wolsit KD-10i	-	-	11.0	-	2022-12-31	196
Other water-borne products						
Wolmanit CX-8	-	18.0	9.0	9.0	2020-12-31	162
Wolmanit CX-8N	-	18.0	9.0		2022-12-31	199
Wolmanit CX-8FP	-	16.0	8.0		2019-12-31	201
Wolmanit CX-8WB	-	18.0	9.0		2020-12-31	191
Wolmanit CX-10	-	15.0	7.0	7.0	2020-12-31	176

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

Wood preservative	Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³ Class**				Approval valid until	Certificate No
	M	A	AB	B		
ORGANIC SOLVENT TYPE						
Triazole products[‡]						
Protim P-Vac 11	-	-	-	26.0/0.41 a.i.	2020-12-31	187
Triazole + IPBC products[‡]						
Gori 605	-	-	-	23.0/0.23 a.i.	2020-12-31	189
CREOSOTE OILS						
Creosote grade A	400	120	80	-	running	EN 13991
Creosote grade B	400	110	80	-	running	EN 13991
Creosote grade C	400	100	70	-	running	EN 13991
MT-kreosot	400	110	80	-	2022-12-31	134

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

‡ The retention requirement is uptake of the formulation/active ingredients (a.i.) in kg per m³ sapwood in the treated zone.